

HITTEBESTENDIGE STAALSOORTEN

	1.4713	X10 Cr Al 7			Z 8 CA 7
	1.4742	X10 Cr Al 18			Z 12 CAS 18
446	1.4762	X10 Cr Al 24	2322		Z 12 CAS 24
309	1.4828	X15 Cr Ni Si 20 12		309 S 24	Z 17 CNS 20.12
310(314)	1.4841	X15 Cr Ni Si 25 20		310 S 31	Z 15 CNS 25.20
310S	1.4845	X12 Cr Ni 25 21	2361	310 S 24	Z 12 CN 25.20